



Aluminumwire
manufactured according
to SS 424 08 02.
International standard
EN 50182.

Machine for rewinding to
the desired length.

Steelreinforced wire on
demand.

Type	Previous type	Area		Number of wires	Diameters		Weight	Tensile strength	Calculated resistance DC at 20°C	Bending Radius
		Nominal	Total		Wire	Conductor				
		mm ²	mm ²		mm	mm				
62-AL1	Vitsippa	62	62,4	7	3,37	10,1	170,6	10,30	0,457	30x
99-AL1	Kattfot	99	99,3	7	4,25	12,8	271,4	15,89	0,287	30x
159-AL1	Gullviva	157	158,6	19	3,26	16,3	435,9	26,17	0,181	30x
241-AL1	Vallmo	241	241,2	19	4,02	20,1	662,8	38,58	0,119	30x
330-AL1	Renfana	329	330,0	37	3,37	23,6	910,2	54,45	0,087	30x
454-AL1	Akleja	454	454,5	61	3,08	27,7	1257,5	74,99	0,063	30x
594-AL1	Hampdån	593	593,6	61	3,52	31,7	1642,4	94,98	0,048	30x
774-AL1	Stormhatt	774	774,2	61	4,02	36,2	2142,1	123,88	0,037	30x
911-AL1	Solros	910	910,7	61	4,36	39,2	2519,8	145,72	0,031	30x